


Lube oil containers

Solution
Luban DMDA-6200

Polymer
HDPE

Process
**Blow Molding, MFR 0.42 g/10 min,
Density 0.953 g/cc**



Car trunk fabric

Solution
Luban HP5101LC

Polymer
PP (Homo)

Process
**Fiber and Filament, MFR 5 g/10 min,
Density 0.91 g/cc**



Seat belts

Solution
Luban HP5101R

Polymer
PP (Homo)

Process
**Fiber and Filament, MFR 24 g/10 min,
Density 0.91 g/cc**



Automotive bumper/ dashboard compound

Solution
Luban EP2340L/EP2340P

Polymer
PP (ICP)

Process
**Injection Molding, MFR 6/15 g/10 min,
Density 0.91 g/cc**



Automotive battery cases

Solution
Luban EP2340P/EP2348R

Polymer
PP (ICP)

Process
**Injection Molding, MFR 15/21 g/10 min,
Density 0.91 g/cc**